


High Temperature Specialty Blend Polytetrafluoroethylene (PTFE)

SPECIFICATIONS

Property	Spec	Value
Tensile Strength (PSI)	DIN 53 455	2030
Elongation (%)	DIN 53 455	120
Hardness (N/mm ²)	DIN 53 456	46
Density (g/cm ³)	DIN 53 479	2.09 +/-0.05
Deformation under load (%)		8.5
15N/mm ² for 100 hrs @ 23° C		
Cylinder dia. 10m x 10mm		
Temperature range	Min	-200° C
	Max	+260° C
Color		Dk. Gray/Black



DESCRIPTION

MT150 is a PTFE material with hardness 46, specially compounded for high temperature applications. Polytetrafluoroethylene (PTFE) has exceedingly strong carbon-fluoride bonds (C-F). PTFE has a simple, linear, flexible and regular molecular structure, which makes it highly crystalline. Commercial PTFE is a high molecular weight polymer. Fluorine atoms form a tight sheath of protection providing PTFE with extreme molecular and physical properties. The sheath prevents PTFE from external influences upon the carbon-carbon backbone. It also results in weak interactions/bindings between polymer chains. These molecular structure properties make PTFE extremely resistant to chemicals or solvents even at very high temperatures and high pressures. PTFE also has very low friction and good anti-stick characteristics. PTFE is tough and flexible even at very low temperatures. However the same molecular structure properties result in mediocre mechanical properties with low stiffness and strength among thermoplastics. PTFE articles cannot be formed with conventional processes for thermoplastics because it does not flow above its crystalline melting point. Parts can be formed by a sintering process under high temperatures.